

PHYSICAL TESTING REPORT

LUCIDEON

insight creating advantage



0013

Sussex Brick Limited
Hastings Brickworks
Fourteen Acre Lane
Three Oaks
Sussex
TN35 4NB

FAO: Mrs. Gemma Barden

Report of Tests on: HL/M-2017

Your Reference: HL/M-2017

Lucideon Reference: (174701)-37476

Date Reported: 14-Nov-2017

Order Number:

Paid by Cheque

Date Logged: 11-Oct-2017

Date(s) of Test(s):

08-Nov-2017 to 09-Nov-2017

Determination of Water Absorption

BS EN 772-21: 2011

	Dry Weight	Saturated Weight After 24 Hr Soak	Water Absorption
No.	g	g	%
1	2195	2544	16
2	2269	2618	15
3	2263	2619	16
4	2278	2636	16
5	2176	2518	16
6	2241	2601	16
7	2261	2629	16
8	2278	2644	16
9	2278	2620	15
10	2165	2514	16
Mean	2240	2594	16

Name of organisation carrying out sampling: SUSSEX BRICK

Method of Sampling: Not Supplied

Opinions and interpretations expressed herein are outside the scope of UKAS Accreditation.

End of Test Report

Miss Zoe Kinally
Manager

This report is issued in accordance with the Conditions of Business of Lucideon Limited and relates only to the sample(s) tested. No responsibility is taken for the accuracy of the sampling unless this is done under our own supervision. This report shall not be reproduced in part without the written approval of Lucideon Limited, nor used in any way as to lead to misrepresentation of the results or their implications.

Lucideon is the trading name of Lucideon Limited. Registered in England No. 1960455.

Lucideon Limited
Queens Road, Penkhull
Stoke-on-Trent
Staffordshire ST4 7LQ

T +44 (0)1782 764428
enquiries@lucideon.com
www.lucideon.com

PHYSICAL TESTING REPORT

Sussex Brick Limited
Hastings Brickworks
Fourteen Acre Lane
Three Oaks
Sussex
TN35 4NB

FAO: Mrs. Gemma Barden

Report of Tests on: HL/M-2017

Your Reference: HL/M-2017

Lucideon Reference: (174701)-37476

Date Reported: 14-Nov-2017

Order Number:

Paid by Cheque

Date Logged: 11-Oct-2017

Date(s) of Test(s):


14-Nov-2017 to 14-Nov-2017

Determination Of Compressive Strength

BS 3921: 1985

	Compressive Strength
No.	N/mm ²
1	19.2
2	19.0
3	16.4
4	15.4
5	17.1
6	16.5
7	14.8
8	15.4
9	22.6
10	17.6
Mean	17.4

End of Test Report



Miss Zoe Kinally
Manager

This report is issued in accordance with the Conditions of Business of Lucideon Limited and relates only to the sample(s) tested. No responsibility is taken for the accuracy of the sampling unless this is done under our own supervision. This report shall not be reproduced in part without the written approval of Lucideon Limited, nor used in any way as to lead to misrepresentation of the results or their implications.

Lucideon is the trading name of Lucideon Limited. Registered in England No. 1960455.

Lucideon Limited
Queens Road, Penkhull
Stoke-on-Trent
Staffordshire ST4 7LQ

T +44 (0)1782 764428
enquiries@lucideon.com
www.lucideon.com